



PRO GROUT™ PLUS

STAIN PROTECTOR

2. MANUFACTURER

PROMA Adhesives Inc.

9801, Parkway, Anjou, Quebec Canada H1J 1P3

Tel.: 514.852.8585

Fax: 514.852.8225

Toll-free: 1 866.51.PROMA (77662)

Email: info@proma.ca

Web: www.proma.ca

3. PRODUCT DESCRIPTION

PRO GROUT™ PLUS is a professional-grade, water-based, powerful additive that mixes with PRO GROUT™ S/U (Sanded/Unsanded) cementitious grouts instead of water to provide increased stain resistance to water and oil –based stains, dirt and grime.

Features

- ♦ Use in place of water for mixing with PRO GROUT S/U (Sanded/Unsanded) cement grouts
- ♦ Protects grout against water and oil-based stains, dirt and grime
- ♦ Grout and seal in one easy step
- ♦ For interior and exterior, commercial and residential applications
- ♦ Maintains application and use characteristics of grout
- ♦ Will not affect grout color
- ♦ Reduces shrinkage of grout
- ♦ Reduces grout water absorption
- ♦ Low VOC
- ♦ Meets or exceeds ANSI A118.7 requirements
- ♦ Contributes to LEED® objectives and requirements

Packaging

850 mL (28.7 fl oz) bottle

Limitations

PRO GROUT™ PLUS maintains all application and use characteristics of the grout it is mixed with, so strictly follow all grout limitations, recommendations and application instructions (see respective technical data sheets for details).

- ♦ Do not use for grouting when chemical and impact resistance is required or for heavy-duty industrial floors.
- ♦ Do not use with epoxy grouts, such as PRO GROUT™ XTREME, premixed grouts or any other grout claiming stain resistance (see respective grout technical data sheets for details).
- ♦ Properly seal porous tile and stone to prevent grout absorption into tile or stone.
- ♦ Efflorescence, a crystalline deposit that sometimes appears over cement grout as a whitish powder or crust, can occur with any ordinary cement-based product.



When mixed with
PRO GROUT™ S or U



- ♦ PRO GROUT™ PLUS will not affect the color of grout, but color variations can occur in any ordinary cement product including grout due to normal slight variations in the product from different batch lot numbers, differing tile types, tile porosity, jobsite and environmental conditions, application and cleaning techniques. Shading, fading and color variations can be minimized by dry pre-blending all the contents from several grout bags or containers together before mixing with PRO GROUT™ PLUS, by proceeding in strict accordance with product instructions and by cleaning with as little water as possible. Avoid acid or chemical cleaning.
- ♦ Do not use with mortars as an additive or with any other cementitious products.
- ♦ Do not mix with other additives.
- ♦ Resists stains under normal use.



4. TECHNICAL DATA

Applicable Standards

For Additional Information, please refer to the most recent TCNA handbook for ceramic tile installation or the TTMAC Specification Guide 09 30 00 Tile Installation Manual, or visit our website at www.proma.ca.

MECHANICAL PROPERTIES (@23°C [73°F] and 50% RH)	
<i>NOTICE: For further information and technical comparisons, consult respective grout data sheets.</i>	
Physical state	Liquid
VOC content	9 g/L
Specific gravity	1.1
Flash point	>200°C (392°F)
Freeze point	0°C (32°F)
pH	7-9
Water absorption % when mixed with PRO GROUT™ PLUS (ANSI A118.7) <i>compared to these products when mixed with water!</i>	
PRO GROUT™ S (SANDED)	Reduced by 30%
PRO GROUT™ U (UNSANDED)	Reduced by 15%
Stain resistance @ 7 DAYS when mixed with PRO GROUT™ PLUS <i>compared to these products when mixed with water!</i>	
PRO GROUT™ S (SANDED)	Increased by 60%
PRO GROUT™ U (UNSANDED)	Increased by 40%
Shelf life	
24 months if kept in its original unopened packaging and stored in a dry location.	

5. INSTALLATION

Surface Preparation

- ♦ Tiles must be firmly secured to a sound solid non-deflecting substrate in accordance with the appropriate ANSI A108 Standard recommendations.
- ♦ The setting mortar or adhesive must be cured and dry in accordance with the "Prior to grouting" product instruction requirements.
- ♦ Remove all spacers, pegs or ropes.
- ♦ Vacuum and clean tile surfaces thoroughly to remove all contaminants.
- ♦ Joint spaces should be uniform in depth and width and free of excess mortar, dust, dirt, free water and debris.
- ♦ Pre-seal tile or stone that can be subject to staining; follow the tile or stone manufacturer's instructions and recommendations.

Mixing

Mixing ratios:

PRO GROUT™ S (SANDED)	
10 kg (22 lb) bag	Mix with 2 bottles of 850 mL (28.7 fl oz) PRO GROUT™ PLUS
5 kg (11 lb) box	Mix with 1 bottle of 850 mL (28.7 fl oz) PRO GROUT™ PLUS

**A small amount of water can be added to get the desired consistency.*

PRO GROUT™ U (UNSANDED)	
10 kg (22 lb) bag	Mix with 4 bottles of 850 mL (28.7 fl oz) PRO GROUT™ PLUS
5 kg (11 lb) box	Mix with 2 bottle of 850 mL (28.7 fl oz) PRO GROUT™ PLUS
2 kg (4.4 lb) box	Mix 680 mL (23 fl oz) [80% of 1 bottle of 850 mL (28.7 fl oz)] PRO GROUT™ PLUS

**A small amount of water can be added to get the desired consistency.*

1. For best results, the same designated person should mix all of the grout.
2. To minimize shading and color variation and to achieve uniform pigment and aggregate dispersion, especially when using several bags or containers from different batch numbers, dry-blend all the powder contents of the bags or containers together before mixing with water.
3. Use clean mixing containers and tools.
4. In the mixing container, pour PRO GROUT™ PLUS additive then gradually add grout powder mix, while mixing slowly (follow mixing ratio recommendations)
5. For better color uniformity, use a measuring container to better control and maintain the same constant proportion of PRO GROUT™ PLUS and grout powder that are mixed. Consistency in the process and in the liquid/powder ratio in batch to batch mixing is paramount to achieving professional results.
6. Mix thoroughly, preferably with a low-speed mixer (max. 450 RPM) until a homogeneous, easy-spread consistency is achieved. Avoid prolonged mixing or air entrapment which may shorten the pot life and cause premature drying, pin-holing and excessive shrinkage.
7. Let the mixture sit still (slake) for about 10 minutes and re-mix without adding any liquid or powder. Re-mix grout periodically while spreading without ever adding water. An excess amount of water used for mixing or cleaning causes weakening, shrinkage, efflorescence and color variation of the grouted joints.
8. Clean tools and hands with water while the product is still fresh.

Application

Apply grout according to selected grout product specifications (see respective technical data sheets for details).

Note: All expansion and control joints must be carried through from substrate to final flooring and filled with an industry-approved flexible sealant, such as PRO COLOR SEAL™ ULTRA, in accordance with ANSI A108.01 norm and TCNA detail EJ171 or TTMAC detail 301MJ. Do not fill or cover expansion and control joints with installation material. Contact PROMA's technical department for additional information.





Curing and Grouting

Refer to respective PROMA cementitious grout data sheets for complete information.

- ♦ Do not step on floors and protect area from foot traffic for at least 24 hours, depending on temperatures and humidity conditions.
- ♦ Protect walls from water contact, impact and vibration for at least 24 hours.
- ♦ Allow at least 24 hours from installation before grouting tiles.

Note: Extended protection and downtime requirements before grouting may be required depending on temperature and humidity conditions and on the porosity and size of the tile or stone being installed.

Cleaning

Clean tools and hands with water while the grout is still fresh.
A neutral cleaner should be used for routine cleaning and daily maintenance.

Health and Safety

Refer to the Safety Data Sheet (SDS) for complete details.

6. AVAILABILITY AND COST

PROMA products are widely available in Canada and the Northeast United States. To find a distributor of PROMA products, call **toll-free: 1.866.51.PROMA (77662)**.

7. WARRANTY

PROMA warrants that this product is manufactured using quality raw materials and is of merchantable quality and suitable for the purpose for which it was intended. PROMA's liability under this warranty shall be limited to the replacement of its product proven to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising from the use of/or the inability to use this product.

8. MAINTENANCE

PRO GROUT™ PLUS, when mixed with PROMA's cementitious grouts, resists dirt and stains, but routine cleaning is still recommended. Avoid acid or chemical cleaning.

PROTECT FROM FREEZING

9. TECHNICAL SERVICE

For more detailed information on this product, please contact our technical department for proper recommendations and job field assistance. **Toll-free: 1.866.51.PROMA (77662)**.

10. FILING SYSTEM

Additional information is available upon request, or by visiting www.proma.ca.



PROMA Adhesives Inc.

9801, Parkway, Anjou, Quebec Canada H1J 1P3

Tel.: 514.852.8585

Fax: 514.852.8225

Toll-free: 1 866.51.PROMA (77662)

Email: info@proma.ca

© 2024 PROMA Adhesives, Inc.

