



# PRO GROUT™ S SANDED

## 2. MANUFACTURER

### PROMA Adhesives Inc.

9801, Parkway, Anjou, Quebec Canada H1J 1P3  
 Tel.: 514.852.8585  
 Fax: 514.852.8225  
 Toll-free: 1 866.51.PROMA (77662)  
 Email: info@proma.ca  
 Web: www.proma.ca

## 3. PRODUCT DESCRIPTION

PRO GROUT™ S (SANDED) is a high-quality, polymer-modified, sanded cement grout that, when mixed with water, provides excellent color consistency and exceptional durability. PRO GROUT S (SANDED) has a super smooth consistency, with sag-free properties and is easier to spread and clean than most conventional grouts.

### Features

- ♦ Use for joints 3 mm (1/8") to 16 mm (5/8")
- ♦ Comes in all PROMA colors
- ♦ Sag-free properties
- ♦ Super smooth consistency
- ♦ Excellent color consistency
- ♦ Easy to use and clean
- ♦ Mixed with PRO GROUT PLUS additive, grout becomes resistant to water and oil-based stains, dirt and grime
- ♦ For interior and exterior institutional, commercial and residential floor and wall tile grouting, even in the most extreme climates
- ♦ For grouting most types of ceramic and porcelain tiles, quarry tiles, pavers, natural and engineered dimension stones, granite and slate
- ♦ Good performance in wet and submerged areas, including water basins, fountains, pools and gang showers
- ♦ Will not promote mold, mildew or bacteria growth
- ♦ No VOC
- ♦ Meets or exceeds ANSI A118.6 and/or ANSI A118.7 requirements
- ♦ Contributes to LEED® objectives and requirements

### Packaging

2 kg (4.4 lb) box; 5 kg (11 lb) box; 10 kg (22 lb) bag; 22.7 kg (50 lb) bag\*

\*Select colors only

### Limitations

- ♦ Do not use for grouting joints less than 1/8" (3 mm) wide [Use PRO GROUT™ U (UNSANDED) instead].
- ♦ Do not use for grouting polished marble or non-vitreous soft glazed wall tiles (See "Caution").
- ♦ Do not use for grouting when chemical, stain and impact resistance is required or for heavy-duty industrial floors. Use PRO GROUT XTREME instead (refer to respective technical data sheet for more information).
- ♦ Do not use when surface and ambient temperatures are below 10°C (50°F) or above 35°C (95°F) or for exterior grouting when rain is expected within 24 hours.
- ♦ **"Caution":** Some types of glazed (or textured) ceramic tiles, porous tiles, marble, limestone and polished stones can be permanently scratched, stained or damaged when grouted with pigmented or sanded grouts. The application of a grout release may be needed to seal prior grouting. Use PROMA's PRO GROUT EASE product prior grouting (see respective technical data sheet for more details).



When mixed with  
PRO GROUT PLUS



Generally, white grout is best suited for grouting white or light colored marble or granite. Certain highly absorptive tiles (such as Saltillo, adobe, terracotta, etc) or tiles with surface porosity, rough textured surface and certain types of porcelain tiles may require sealing prior to grouting to prevent staining. Test a small area first, taking all the necessary precautions; apply, where required, an appropriate grout release (such as PROMA's PRO GROUT EASE - refer to technical data sheet for more details) to prevent grout staining. Follow the tile or stone manufacturer's instructions and recommendations.

- **Efflorescence**, a crystalline deposit that sometimes appears over cement grout as a whitish powder or crust, can occur with any ordinary cement-based product.
- **Color variations** can occur in any ordinary cement product including grout due to normal slight variations in the product from different batch lot numbers, differing tile types, tile porosity, jobsite and environmental conditions, application and cleaning techniques. Shading, fading and color variations can be minimized by dry pre-blending all the contents from several grout bags or containers together before mixing with water, by proceeding in strict accordance with product instructions and by cleaning with as little water as possible.
- Avoid acid or chemical cleaning.





## 4. TECHNICAL DATA

### Applicable Standards

For Additional Information, please refer to the most recent TCNA handbook for ceramic tile installation or the TTMAC Specification Guide 09 30 00 Tile Installation Manual, or visit our website at [www.proma.ca](http://www.proma.ca).

WORKING PROPERTIES (@23° C [73° F] and 50% RH)	
Pot life	> 1 hour
Lead time prior initial clean up	15-30 minutes
Lead time prior to light traffic	12-24 hours
Lead time prior to heavy traffic	72 hours
Lead time prior to water immersion or freeze/thaw	21 days
Lead time prior to sealing	21 days

PHYSICAL PROPERTIES (@23° C [73° F] and 50% RH)	
VOC content	0 g/L
Density (paste)	1.8 g/mL
PH	11-13
<b>Compressive strength @ 28 days as per ANSI A118.6/A118.7</b>	
<b>ANSI requirements</b>	<b>Results</b>
> 3000 PSI (21 MPa)	> 3500 PSI (24 MPa)
<b>Linear shrinkage @ 27 days as per ANSI A118.6/A118.7</b>	
<b>ANSI requirements</b>	<b>Results</b>
< 0.2%	0.15%
<b>Water absorption (%) as per ANSI A118.7</b>	
<b>ANSI requirements</b>	<b>Results</b>
< 5%	4.5%
<b>Approximate coverage</b>	
Visit our web site <a href="http://www.proma.ca">www.proma.ca</a> and refer to our <b>GROUT CALCULATOR</b> to help determine the approximate amount of grout needed for any sized job.	
<b>Shelf life</b>	
12 months if kept in its original unopened packaging and stored in a dry location.	

## 5. INSTALLATION

### Surface Preparation

- Tiles must be firmly secured to a sound solid non-deflecting substrate in accordance with the appropriate ANSI A108 Standard recommendations.
- The setting mortar or adhesive must be cured and dry in accordance with the "Prior to grouting" product instruction requirements.
- Remove all spacers, pegs or ropes.
- Vacuum and clean tile surfaces thoroughly to remove all contaminants.
- Joint spaces should be uniform in depth and width and free of excess mortar, dust, dirt, free water and debris.
- Pre-seal tile or stone that can be subject to staining; follow the tile or stone manufacturer's instructions and recommendations. Use PROMA's PRO GROUT EASE product prior to grouting (see respective technical data sheet for more details).

### Mixing

#### Mixing Ratio: 3 1/2 parts powder to 1 part water (by volume)

1. For best results, the same designated person should mix all of the grout.
2. To minimize shading and color variation and to achieve uniform pigment and aggregate dispersion, especially when using several bags or containers from different batch numbers, dry-blend all the powder contents of the bags or containers together before mixing with water.
3. Use clean mixing containers and tools.
4. In the mixing container, measure and pour clean cool water and gradually add PRO GROUT S (SANDED) powder mix, while mixing slowly, using the following approximate ratios:

Water	PRO GROUT S (SANDED)
340 mL (11.5 US fl. Oz.)	2 kg (4.4 lb) box
850 mL (28.7 US fl. Oz.)	5 kg (11 lb) box
1.7 L (0.45 gal, 1.8 US quarts)	10 kg (22 lb) bag
3.9 L (1 gal, 4.1 US quarts)	22.7 kg (50 lb) bag

5. For better color uniformity, use a measuring container to better control and maintain the same constant proportion of water and grout powder that are mixed. Consistency in the process and in the water/powder ratio in batch to batch mixing is paramount to achieving professional results.
6. Mix thoroughly, preferably with a low-speed mixer (max. 450 RPM) until a homogeneous, easy-spread consistency is achieved. Avoid prolonged mixing or air entrapment which may shorten the pot life and cause premature drying, pin-holing and excessive shrinkage.
7. Let the mixture sit still (slake) for about 5 minutes and re-mix without adding any water or powder. Re-mix grout periodically while spreading without ever adding water. An excess amount of water used for mixing or cleaning causes weakening, shrinkage, efflorescence and color variation of the grouted joints.

**Note:** Use PRO GROUT PLUS to obtain stain resistant grout against water and oil-based stains, dirt and grime.

### Application

**Note:** Installation procedure should conform to ANSI A108.10 Standard recommendations.

1. Lightly dampen absorptive, highly porous tile or stone with clean, cool water but leave no standing water in the open joint space or use PROMA's PRO GROUT EASE product (see respective technical data sheet for more details).
2. With a firm sharp-edge rubber float held at a 45° angle, force grout diagonally into the joint, ensuring that the grout is well-compacted, free of voids and pin holes, and filled flush with the tile or stone edge.
3. Remove excess grout through successive diagonal passes using the edge of the rubber float held at a sharp 90° angle.
4. Allow grout to harden sufficiently to sustain only slight finger-nail indentation when pressed hard or approximately 15 to 30 minutes depending on the type of tile or stone and ambient temperature and humidity conditions.
5. Use as little water as possible for cleaning up grout. An excess amount of water used for mixing or cleaning causes weakening, shrinkage, efflorescence, pin holes and color variation of the grouted joints.





6. Smooth and level joints and remove excess grout from tile or stone with a slightly damp (NOT WET) soft close pore cellulose sponge, wiping lightly and delicately in diagonal strokes. Change water and rinse sponge frequently. Keeping the water and sponge clean will achieve better joint color uniformity.
7. Wait at least 2 to 3 hours before removing the final haze from the tile or stone surface with a soft dry white or neutral cloth. [Removal of the dry grout haze from unglazed or unpolished stone surfaces can also be successfully achieved by using a white (fine grain) nylon scouring pad]. DO NOT ACID WASH.

### Expansion and Control Joints

- ◆ Install control joints where tiles abut restraining surfaces, around the perimeter of the work and at the base of columns and curbs.
- ◆ Install and space expansion and control joints in all directions in accordance with TCNA HANDBOOK FOR CERAMIC TILE INSTALLATION Detail #EJ-171 recommendations, or TTMAC Specification Guide 09 30 00 Detail #301-MJ recommendations. CAUTION: DO NOT cut EXPANSION JOINTS in after the tiles have been installed. Install tiles normally and stop when the control joint location is reached. Cut the tile if required and resume setting from the opposite side of the joint. Before proceeding further, rake the joint and leave the tile and joint space clean.
- ◆ DO NOT FILL EXPANSION JOINT SPACE UNTIL GROUTING IS COMPLETED on the remainder of the job.
- ◆ Install a suitable industry-approved compressible bead and flexible sealant to caulk expansion and control joints. Follow the sealant manufacturer's installation instructions.

### Curing and Protection

- ◆ Grout must be fully cured before regular cleaning.
- ◆ Protect from weather, freezing, excessive heat and complete water immersion for at least 21 days (or as required by the setting mortar or adhesive instructions).
- ◆ Floors: Protect floors from foot traffic for at least 24 hours and from heavy commercial or industrial traffic for at least 72 hours.
- ◆ Walls: Protect walls from impact and vibration for at least 24-72 hours (or as required by the setting mortar or adhesive instructions).
- ◆ Showers, pools, fountains, basins, etc.: Do not fill pools or fountains for at least 21 days after installation. For residential showers or tub surrounds, wait 24-48 hours after grouting and 14 days for steam showers.
- ◆ Temperature and humidity conditions affect the curing of all cement-based products. Allow for extended curing and protection periods at lowering temperatures under 15°C (60°F) and/or when the ambient relative humidity is higher than 70%.

### Cleaning

Clean tools and hands with water while the product is still fresh.

### Health and Safety

Refer to the Safety Data Sheet (SDS) for complete details.

### 6. AVAILABILITY AND COST

PROMA products are widely available in Canada and the Northeast United States. To find a distributor of PROMA products, call **toll-free: 1.866.51.PROMA (77662)**.

### 7. WARRANTY

PROMA warrants that this product is manufactured using quality raw materials and is of merchantable quality and suitable for the purpose for which it was intended. PROMA's liability under this warranty shall be limited to the replacement of its product proven to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising from the use of/or the inability to use this product.

### 8. MAINTENANCE

Product requires no special maintenance.

### 9. TECHNICAL SERVICE

For more detailed information on this product, please contact our technical department for proper recommendations and job field assistance. **Toll-free: 1.866.51.PROMA (77662)**.

### 10. FILING SYSTEM

Additional information is available upon request, or by visiting [www.proma.ca](http://www.proma.ca).



---

**PROMA Adhesives Inc.**

9801, Parkway, Anjou, Quebec Canada H1J 1P3

Tel: 514.852.8585

Fax: 514.852.8225

Toll-free: 1 866.51.PROMA (77662)

Email: [info@proma.ca](mailto:info@proma.ca)

© 2016 PROMA Adhesives, Inc.